



Test Report # BRUSHEDMETLAMB-0001-122716

TOWNSEND LEATHER NFPA 260 COVER FABRIC BURN REPORT

Date: 12/27/2016

Conditioning Chamber: Time In: 11am Time Out: 12:34 PM
12/21/2016 12/27/2016

THICKNESS: 1.0 - 1.1 MM

Specimen: Townsend Leather Brushed Metallic Lambskin
(Additional Flametreatment)

Standard Filling Material: Non FR polyurethane foam, density 20 kg/m³ to 25 kg/m³

Test

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	No	10.16
2	No	12.70
3	SE	10.16

Retest

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
3	SE	5.08

Retest 2

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
3	SE	5.08

CLASS I **CLASS II**

Tested according to NFPA 260 : 2013 Edition-Section 6.1 Cover Fabric Test

Dawn Finch

Quality Control

Townsend Leather Co. Inc.

45-49 Townsend Ave PO Box 669

PO Box 669

Johnstown, NY 12095

This form is electronically signed. If you need an actual signature, please call.