



Test Report # **HER-0001-91015**

TOWNSEND LEATHER NFPA 260 COVER FABRIC BURN REPORT

Date: **9/10/2015**

Conditioning Chamber: Time In: 11:25am Time Out: 1:30pm
9/9/2015 9/10/2015

THICKNESS: 1.0 - 1.2 MM

Specimen: **Townsend Leather** **Heritage Cowhide**

Standard Filling Material: Non FR polyurethane foam, density 20 kg/m³ to 25 kg/m³
Test

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	SE	5.08
2	SE	5.08
3	SE	7.62

Retest

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	SE	5.08
2	SE	5.08
3	SE	10.16

Retest 2

Specimen # (Seconds)	Ignition (yes/no/SE)	Char Length on Vertical Panel (mm)
1	SE	5.08
2	SE	5.08
3	SE	7.62

CLASS I **CLASS II**

Tested according to NFPA 260 : 2013 Edition-Section 6.1 Cover Fabric Test

Dawn Finch

Quality Control

Townsend Leather Co. Inc.

45-49 Townsend Ave PO Box 669

PO Box 669

Johnstown, NY 12095

This form is electronically signed. If you need an actual signature, please call.